

PRODUCT DESCRIPTION

Stonshield HRI is a nominal 5 mm thick durable flooring system with a decorative, slip resistant surface. Its troweled base provides superior impact resistance and allows the Stonshield HRI to be applied over rough substrates. The color quartz broadcast topshield layer results in an attractive floor surface that is textured for safety. This seamless overlayment has no joints or seams to harbor dirt and bacteria and resists attack by most acids and alkalis. It is comprised of:

Stonshield HRI base

A three-component, troweled mortar base consisting of epoxy resin, curing agent and finely graded silica aggregate

Stonshield Undercoat

A two-component, free flowing epoxy formulation consisting of resin and curing agent

Stonshield Aggregate

Brightly colored, quartz broadcast aggregate

Stonkote CE4

A two-component, high performance, UV resistant, clear epoxy sealer.

OPTIONS

Waterproofing

Where the total system must be waterproof, use of Stonhard's Stonproof ME7 membrane system is required with strict adherence to application instruction.

Cove Base

To provide for an integral seal at the joint between the floor and the wall, cove bases in heights from 5 to 15 cm are available.

Standard or Medium Texture

Stonkote CE4 is applied at a thickness that will produce the desired texture.

PACKAGING

Stonshield HRI is packaged in units for easy handling. Each unit consists of:

Stonshield HRI base

2 cartons, each containing:

6 foil bags of Amine

6 poly bags of Resin

12 individual bags of aggregate

Stonshield Undercoat

0.75 carton, containing:

6 foil bags of Amine

6 poly bags of Resin

0.75 carton containing

6 bags of aggregate

Stonshield Aggregate

3 individual bags of colored quartz aggregate

PHYSICAL CHARACTERISTICS

Compressive Strength (ASTM C579)	70 N/mm ² after 7 days
Tensile Strength (ASTM C-307)	11 N/mm ²
Flexural Strength (ASTM C-580)	30 N/mm ²
Flexural Modulus of Elasticity (ASTM C-580)	1.38 x 10 ⁴ N/mm ²
Hardness (ASTM, D-2240, Shore D)	85 to 90
Impact Resistance (ASTM D-2794)	> 18 Nm
Abrasion Resistance (ASTM D-4060, CS-17)	0.06 gm *
Flammability (ASTM E-648)	Class I
Thermal Coefficient of Linear Expansion (ASTM C-531)	1.8 x 10 ⁻² mm/m°C
Water Absorption (ASTM C-413)	0.1%
VOC Content (ASTM D-2369)	Stonshield HRI Base - 40 g/l Stonshield Undercoat - 34 g/l Stonkote CE4 - 34 g/l
Cure Rate (@ 77°F/25°C)	12 hours for Foot traffic 24 hours for normal operations

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab made test coupons.

Stonkote CE4

Standard texture

0.75 carton containing:

6 foil bags of Amine

6 poly bags of Resin

Medium texture

1 carton containing:

6 foil bags of Amine

6 poly bags of Resin

USGBC LEED RATING

Stonshield HRI meets the requirements of LEED;

- MR Credit 1 – Building Reuse
- MR Credit 2 – Construction Waste Management
- IEQ Credit 4 – Low Emitting Materials
- VOC content of the total system <100 g/l

COVERAGE

Each unit of Stonshield HRI will cover approximately 27.9 m² of surface at a nominal 5 mm thickness.

STORAGE CONDITIONS

Store all components of Stonshield HRI between 16 to 30°C in a dry area. Avoid excessive heat and do not freeze.

The shelf life is 3 years in the original, unopened container.

COLOR

Stonshield HRI is available in 2 solid colors and 10 tweed pattern standard colors. Refer to the Stonshield color sheet. Custom colors are available upon request.

SUBSTRATE

Stonshield HRI, in conjunction with its appropriate primer, is suitable for application over properly prepared concrete, both new and old. It is also designed for renovation work over wood or sound brick and quarry tile. Stonshield HRI is not recommended over asphalt, mastic, gypsum based products or painted surfaces. These must first be removed by mechanical means prior to priming and overlayment.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard's representative or Technical Service.

APPLYING

- DO NOT attempt to install material if the temperature of Stonshield HRI components and substrate are not within 16 to 30°C. The cure time and application properties of the material are severely affected by temperatures outside of this range.
- Stonshield HRI Base is mixed, screed applied and troweled to a tightly closed finish. Allow for at least an 8 hour cure.
- Next, lightly grind the HRI Base. Then the Stonshield Undercoat is mixed and applied to the floor surface using a steel squeegee and looped roller to uniformly distribute the material and promote surface leveling
- Stonshield Aggregate is broadcast into the freshly rolled Undercoat using a Stonhard Spraycaster to ensure even distribution of the aggregate. Allow at least 8 hours to cure.
- Scrape the floor with a steel squeegee, sweep to remove loose aggregate, then vacuum.
- Stonkote CE4 is then mixed and applied. For a standard texture, the sealer is applied using a rubber squeegee and then rolled using a medium nap roller. For a medium texture, the sealer is applied using a rigid rubber squeegee and then rolled using a saturated medium nap roller.


Refer to the Stonshield HRI Directions for further detail.

NOTES

- Procedures for cleaning of the flooring system during operations can be found in the Stonhard Floor Maintenance Guide.
- Specific information regarding chemical resistance is available in the Stonshield Chemical Resistance Guide.
- Material Safety Data Sheets for Stonshield HRI are available on line at www.stonhard.com under Products or upon request.
- A staff of technical service engineers is available to assist with installation or to answer questions related to Stonhard products.
- Requests for literature can be made through local sales representatives and offices, or corporate offices located worldwide.

CE MARKING

The harmonized European Standard EN 13813 „Screed material and floor screeds- Screed materials - Properties and requirements“ specifies the requirements for screed materials for use in floor construction internally. Resinous flooring systems as well as resinous screeds fall under this specification they have to be CE-labeled as **per Annex ZA., Table ZA.1.5 and 3.3** and fulfill the requirements of the given mandate of the Construction Products Regulation no. 305/2011

	
StonCor Europe Rue du Travail 9 1400 Nivelles, Belgium	
13	
EC-DOP-2013.05.002	
EN 13813 SR-AR1.0-B2.0-IR18	
Synthetic resin flooring system for use internally in buildings (system as per Product Data Sheet)	
Release of corrosive substances:	SR
Wear resistance:	AR1.0
Adhesion strength by pull-off test:	>B2.0
Impact resistance:	IR18
Chemical resistance:	CRG*
* CRG: see Stonhard Chemical Resistance Guide	

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

STONHARD A Division of **StonCor**^{Group}

www.stoncor-europe.com

Belgium	+32 67493710	Spain/Portugal	+351 707200088	Germany	+49 240541740
France	+33 160064419	United Kingdom	+44 1256336600	The Netherlands	+31 165585200
Poland	+48 422112768	East Europe	+31 165585200	Italy	+39 02253751